

# **QPL 25 PRESSURE INJECTED EPOXY SYSTEMS**

## **PRESSURE INJECTED EPOXY SYSTEMS**

### **PROCEDURES**

#### **GENERAL**

This evaluation procedure outlines the Department's approval process for pressure injected epoxy systems used to make structural repairs to cracked concrete and other materials.

#### **SPECIFICATIONS**

ASTM C 881 and 882

#### **PROCEDURES**

A completed Product Evaluation Form, MSDS sheets, if applicable, product data information and a sample of the product being tested must be submitted to the Division of Materials and Tests.

The product will be mixed according to the manufacturer's recommendations and must meet the following requirements.

Slant Shear Hardened to Hardened Concrete

Age	PSI
2 Day	1000
14 Days	1500